



- Titanium White
- Tinting White (Pearl/Titanium)
- Naples Yellow
- Jaune Brillant
- Naples Yellow Reddish
- Transparent Yellow
- Arylamide Yellow Light
- Cadmium Yellow Light
- Cadmium Yellow Medium
- Indian Yellow
- Cadmium Yellow Deep

- Arylamide Yellow Deep
- Orange
- Cadmium Orange
- Transparent Perinone Orange
- Vermilion
- Red Gold
- Napthol Red Light
- Cadmium Red Light (Scarlet)
- Pyrrole Red
- Napthol Crimson
- Cadmium Red Medium

- Crimson
- Permanent Alizarine
- Quinacridone Magenta
- Brilliant Magenta
- Quinacridone Red Violet
- Mars Violet
- Dioxazine Purple
- Brilliant Violet
- Purple
- French Ultramarine Blue
- Pacific Blue

- Pthalo Blue (Red Shade)
- Pthalo Blue
- Prussian Blue Hue
- Cobalt Blue
- Cobalt Blue Hue
- Cerulean Blue
- Cerulean Blue Hue
- Pthalo Turquoise
- Cobalt Turquoise Light
- Cobalt Turquoise Light Hue
- Cobalt Green

- Cobalt Green Hue
- Terre Verte
- Forest Green
- Permanent Sap Green
- Permanent Green Light
- Olive Green
- Chromium Green Oxide
- Yellow Ochre
- Transparent Red Oxide
- Light Red Ochre
- Burnt Sienna

- Indian Red Oxide
- Permanent Brown Madder
- Raw Umber
- Permanent Sap Green
- Raw Sienna Dark
- Burnt Umber
- Brown Black
- Red Black
- Blue Black (Indigo)
- Green Black
- Carbon Black
- Mars Black

- Paynes Grey
- Toning Grey Mid
- Toning Grey Yellowish
- Toning Grey Pinkish
- Silver
- Pale Gold
- Rich Gold
- Copper

See page 2 for pigment and lightfastness specifications.

Colour	ASTM	BSL	Pigment	Col No.
 Titanium White	1	8:8:8	PW.6	1111
 Tinting White (Pearl/Titanium)	N/T	8:8:8	PW.6, MICACEOUS	1112
 Naples Yellow	1	7:6-7:6	PW.6, PY.42, PY74LF	0134
 Jaune Brillant	1	7:6-7:6	PW.6, PY.74LF, PR.9	1485
 Naples Yellow Reddish	1	7:6-7:6	PW.6, PY.65, PR.9	1625
 Transparent Yellow	2	7-8:7-8:6-7	PY.74	0109
 Arylamide Yellow Light	1	7-8:7-8:6-7	PW.6, PY.74LF	0012
 Cadmium Yellow Light	1	8:8:8	PY.35	0102
 Cadmium Yellow Medium	1	8:8:8	PY.37	0116
 Indian Yellow	2	7-8:7-8:6	PY.74, PR.101	0137
 Cadmium Yellow Deep	1	8:8:8	PY.37	1375
 Arylamide Yellow Deep	1	7:6-7:6	PW.6, PY.65	1235
 Orange	2	6:5-6:5	PY.65, PO.5, PO.20	1665
 Cadmium Orange	1	8:8:8	PO.20	0021
 Transparent Perinone Orange	1	8:8:7-8	PO.73	1655
 Vermilion	2	6:5-6:5	PO.5	0172
 Red Gold	1	7:8-7:8	PY.74, PR.175	0167
 Naphthol Red Light	1	7:6-7:6	PR.9	0032
 Cadmium Red Light (Scarlet)	1	8:8:8	PR.108	1795
 Pyrrole Red	1	8:8:8	PR.254	0485
 Naphthol Crimson	2	6:5:4-5	PR.170	0187
 Cadmium Red Medium	1	8:8:8	PR.108	0194
 Crimson	N/T	7-8:6-7:6	PR48.4	0186
 Permanent Alizarine	1	8:8:8	PR.175, PR.122	0202
 Quinacridone Magenta	1	8:8:8	PR.122	0221
 Brilliant Magenta	1	8:8:8	PR.122, PW.6	0240
 Quinacridone Red Violet	1	8:8:8	PV.19	0512
 Mars Violet	1	8:8:8	PR.101	0504
 Dioxazine Purple	2	8:8:8	PV.23RS	2685
 Brilliant Violet	2	-:7-8:7-8	PW.6, PV.23RS	0527
 Purple	N/T	7:6-7:6	PR48.4, PB15.3	2675
 French Ultramarine Blue	1	8:8:8	PB.29	0072
 Pacific Blue	2	-:7-8:7	PW.6, PV.23RS, PB.15.3	2718
 Pthalo Blue (Red Shade)	1	8:8:8	PB.15	0294
 Pthalo Blue	1	8:8:8	PB.15.3	2795
 Prussian Blue Hue	1	8:8:7-8	PB.15, PR.175	0296
 Cobalt Blue	1	8:8:8	PB.28	0286
 Cobalt Blue Hue	1	8:8:8	PB.29, PW.6, PB.15	2728

Colour	ASTM	BSL	Pigment	Col No.
 Cerulean Blue	1	8:8:8	PB.28, PG.50	2935
 Cerulean Blue Hue	1	8:8:8	PB.29, PB.15.3, PW.6, PG.7	2936
 Pthalo Turquoise	1	8:8:8	PB.15.3, PG.7	0315
 Cobalt Turquoise Light	1	8:8:8	PG.50	0326
 Cobalt Turquoise Light Hue	1	8:8:8	PB.15.3, PW.6, PG.7	0327
 Cobalt Green	1	8:8:8	PG.50	0348
 Cobalt Green Hue	2	7-8:7-8:6-7	PW.6, PY.74, PG.7	0356
 Pthalo Green	1	8:8:8	PG.7	3292
 Terre Verte	1	8:8:8	PBr.7:PB.15.3	0357
 Forest Green	2	7-8-7:8-7:6	PY.74, PB.15.3, PR.101	5467
 Permanent Sap Green	2	7-8:7-8:6-7	PY.74, PB.15.3	0364
 Permanent Green Light	1	7-8:7-8:6-7	PY.74LF, PG.7	0361
 Olive Green	2	7:6-7:6	PY.74, PBk.7	5815
 Chromium Green Oxide	1	8:8:8	PG.17	7483
 Yellow Ochre	1	8:8:8	PY.42	0131
 Transparent Red Oxide	1	8:8:8	PR.101	0491
 Light Red Ochre	1	8:8:8	PR.101	0174
 Burnt Sienna	1	8:8:8	PBr.7	0483
 Indian Red Oxide	1	8:8:8	PR.101	1817
 Permanent Brown Madder	1	8:8:7	PR.175	0188
 Raw Umber	1	8:8:8	PBr.7	0462
 Raw Sienna Dark	1	8:8:8	PBr.7	0154
 Burnt Umber	1	8:8:8	PBr.7	0005
 Brown Black	1	8:8:8	PR.101, PBk.7	0440
 Red Black	2	7-8:6-7:6	PR.112, PBk.7	0412
 Blue Black (Indigo)	1	8:8:8	PB.15.3, PBk.7	5395
 Green Black	1	8:8:8	PG.7, PBk.7	5605
 Carbon Black	1	8:8:8	PBk.7	0000
 Mars Black	1	8:8:8	PBk.7	0004
 Paynes Grey	1	8:8:8	PB.29:PBk.7	0533
 Toning Grey Mid	1	8:8:8	PW.6, MICACEOUS	0428
 Toning Grey Yellowish	1	8:8:8	PW.6, PBr.7	0467
 Toning Grey Pinkish	1	8:8:8	PW.6, PBk.7	0691
 Silver	N/T	8:8:8	ALUMINIUM	0877
 Pale Gold	N/T	7-8:7-8:7-8	MICACEOUS	0871
 Rich Gold	N/T	8:8:8	MICACEOUS	0873
 Copper	N/T	8:8:8	MICACEOUS	0876